



AURELIA® SONIC 100

2.2mil, Nitrile Powder Free Examination Gloves


AURELIA® GLOVES

sales@supermax.co.uk
01733 615215

Supermax Healthcare Ltd
Unit 12-16 Titan Drive
Fengate, Peterborough
PE1 5XN



Regulations	PPE Regulation (EU) 2016/425 Medical Device Regulation (EU) 2017/745, 93/42/EEC
Quality Standards	ISO 9001:2015 Quality Management Systems. ISO 13485: 2016 Medical Devices Quality Management Systems.
Harmonised Standards	BS EN ISO 374 - 1 Protective gloves against dangerous chemicals, Type B, JKT. BS EN ISO 374 - 5 Protective gloves against microorganisms (Virus). BS EN 455 1-4 Medical gloves for single use. EN 420: 2003 + A1: 2009 Protective gloves. General requirements and test methods. BS EN 1186:2002 Materials and articles in contact with foodstuffs.



Sizes & Dimensions	Single Wall Thickness	Physical Properties													
<p>XS 70±10 mm S 80±10 mm M 95±10 mm L 110±10 mm XL > 110 mm</p>	<p>min. 240 mm min. 240 mm min. 240 mm min. 240 mm min. 240 mm</p>	<p>① min. 0.09mm ② min. 0.05mm ③ min. 0.05mm</p>	<table border="1"> <thead> <tr> <th></th> <th>Unaged</th> <th>Aged</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength</td> <td>Min. 14.0 MPa</td> <td>Min. 14.0 MPa</td> </tr> <tr> <td>Elongation</td> <td>Min. 500%</td> <td>Min. 400%</td> </tr> <tr> <td>Strength at Break</td> <td>Min. 6N</td> <td>Min. 6N</td> </tr> </tbody> </table>		Unaged	Aged	Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa	Elongation	Min. 500%	Min. 400%	Strength at Break	Min. 6N	Min. 6N
	Unaged	Aged													
Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa													
Elongation	Min. 500%	Min. 400%													
Strength at Break	Min. 6N	Min. 6N													



Nitrile



Powder Free



5 Years



Finger Textured



3.2g +/- 0.2g



Colbalt Blue

